

## Antibacterial and Anti-Fungal Activity of (Tetrahalo Metallate) Copper and Nickel Nanoparticles Stabilized by Cationic Thiol Polyurethane Surfactants

Mostafa E.Hendawy<sup>1\*</sup>, Nabel A. Negm<sup>2</sup>, Mohamed F. Zaky<sup>2</sup>, Ibrahim A.Sabbah<sup>1</sup>

<sup>1</sup>Chemistry Department, Faculty of Science, Al-Azhar University, Egypt

<sup>2</sup>Petrochemicals Department, Egyptian Petroleum Research Institute

**\*Corresponding Author:** Mostafa E.Hendawy, Chemistry Department, Faculty of Science, Al-Azhar University, Egypt

**Abstract:** Copper and nickel nanoparticles are known to be one of the multifunctional inorganic nanoparticles with effective antibacterial activity. This study aims to determine the antimicrobial efficacy of chemical synthesized copper and nickel nanoparticle against various bacterial and fungal pathogens. Grinding method is used to synthesize copper and nickel nanoparticles. In this paper, the new cationic thiol polyurethane surfactants with different alkyl chain length were synthesized (PQ8, PQ10 and PQ12). The chemical structure of the synthesized surfactants was confirmed using infra-red spectroscopy (IR) and proton nuclear magnetic resonance spectroscopy (<sup>1</sup>H NMR). The nanostructure of the synthesized surfactant with copper and nickel nanoparticles with diameters ranging from 10 to 55 nm was prepared and characterized using ultra violet spectrophotometer (UV), infra-red spectroscopy (IR) and transmission electron microscope (TEM). The results declare formation and stabilization of copper and nickel nanoparticle using synthesized cationic surfactants. Antimicrobial activity of the synthesized cationic surfactants and their nanostructure with copper and nickel nanoparticles were evaluated against pathogenic bacteria and fungi. The antimicrobial activity showed the enhancement in the antimicrobial activity of the synthesized cationic surfactants in the nanostructures form.

**Keywords:** Polyurethane, Cationic Surfactants, Copper Nanoparticles, Nickel Nanoparticles, Antimicrobial Activity, Transmission Electron Microscope.

### 1. INTRODUCTION

Cationic polyurethane dispersions, which are prepared by incorporating a tertiary amine diol or polyol followed by treatment with an acid, are seldom used commercially. One potential advantage of cationic polyurethane dispersions is that they have been found to exhibit excellent adhesion properties. However, the antibacterial properties of cationic polyurethane dispersions are of much greater interest. Cationic compounds are able to bind to bacteria and other microbes and disrupt cell structure, resulting in permeabilization and death [1].

Polymeric materials containing quaternary ammonium have been extensively studied and used in antibacterial-relevant application [2]. It's found that the positively charged quaternary ammonium groups destructively interact with negatively charged bacterial cells and/or cytoplasmic membranes. The rise of quaternary ammonium groups improves the antibacterial activity of the polyurethane dispersions [3].

In recent years, the synthesis and utilization of novel antimicrobial cationic surfactants and their nanoparticles has increased due to the gradual increase of drug resistance among microorganisms. For this reason, copper and nickel compounds have also been employed as antimicrobial and antifungus agents. By using nanotechnology, which enhances the antimicrobial activity of copper and nickel metal by manipulating it to the nanoparticles, copper and nickel nanoparticles have been widely used to control bacterial and fungal diseases. [4-5].

Copper, nickel and the compounds of Au, Ag, Pd and Pt are widely used in these days. Copper and nickel have an excellent electrical conductivity. Due to relatively low costs, this metal plays a significant role in modern electronic circuit [6]. Because of its excellent electrical conductivity, catalytic behaviour, good compatibility and surface enhanced Raman scattering activity. Copper and

nickel nanoparticles have drawn the attention of scientists to be used as essential component in the future nano-devices [7]. Cu and Ni nanowires are used in nanoelectronics and have application possibilities for magnetic devices, nanosensors, electron emitters and other electronic applications. Cu and Ni nanoparticles have been explored to be used as nanoprobes in medicines and bio-analytical areas [8-9].

The emergence of nanoscience and nanotechnology in the last decade presents opportunities for exploring the bactericidal effect of metal nanoparticles. The bactericidal effect of metal nanoparticles has been attributed to small size and high surface to volume ratio, which allows them to interact closely with microbial membranes and not merely due to the release of metal ions in solution [10].

In the present study stable copper and nickel nanoparticles with narrow size and homogenous distribution were synthesized by grinding method and cationic thiol polyurethane surfactants used as a capping agent. Even today, the exact mechanism of antimicrobial action of the CuNPs remains unknown. The general view seems to be a combination of several factors: releasing  $\text{Cu}^{+2}$  ions, their penetration and disruption cell membrane and biochemical pathway by chelating cellular enzymes and DNA damage [11-12].

Previously reported antibacterial activity of copper nano particle, it was found that it has significant potency to act as bacteriocidal agent than gold, silver, zinc nano particles. Combination of different nano particles such as silver and copper may show more significant effect on bacterial growth. Gram-positive bacteria have a thick cell wall containing multiple layers of peptidoglycan, while gram-negative bacteria have a relatively thin cell wall consisting of a single layer of peptidoglycan. Surfaces of copper nano particles interact directly with the bacterial cell wall and outer membrane, leads to rupture of cell wall and killing bacteria [13-14].

## **2. EXPERIMENTAL METHODS**

### **2.1. Materials**

Fatty alcohols (Octanol, Decanol and Dodecanol) were purchased from Sigma, Germany. Toluene diisocyanate TDI (97 %) was purchased from DOW, USA. Mercapto acetic acid, Bromoacetic acid and Sodium borohydride were purchased from Aldrich, Germany. Copper Chloride and Nickel chloride were purchased from BDH, British. Triethanol amine and solvents were obtained from ADWIC chemicals company, Egypt.

### **2.2. Synthesis**

#### *2.2.1. Preparation of Triethanol Amine Mono Mercaptoacetate*

Triethanol amine (0.1 mole) and mercaptoacetic acid (0.1 mole) were charged in 250 mL round flask in presence of xylene (75 mL) as a solvent and *p*-toluene sulfonic acid (0.1 g) as a dehydrating agent. The completion of the reaction was monitored by obtaining 0.1 mole of  $\text{H}_2\text{O}$  (1.8 mL) [15]. At the end of the reaction, the solvent was removed by evaporated by the effect of evacuation, while *p*-toluene sulfonic acid was eliminated from the reaction medium by take out the obtained esters by dissolving in ether (diethyl ether). The evaporated solvent was recovered and purified to reuse. The unreacted and excess reactants were eliminated from the products by successive sanitization of the crude products to afford triethanol amine mono mercaptoacetate in a yield of 96%.

#### *2.2.2. Preparation of Thiol Polyurethane (P)*

Thiol polyurethane polymerization reaction was carried out in a suitable flat bottom glass reactor (500 mL) connected to a mechanical rotor, dropping funnel, thermometer and condenser. Inside the reaction vessel, a mixture of toluene diisocyanate (TDI) (0.1 mole) dissolved in methyl ethyl ketone (50 mL), triethanol amine mercaptoacetate (0.2 mole) and five drops of triethylene diamine dropped during 20 min was mixed [16]. The reaction medium was continuously mixed at 30 °C for 30 min to obtain the pre-polymer. The ratio of isocyanates (NCO) to reactive hydroxyl group (OH) was reserved at 1:2 in polyurethane reaction polymerization. The prepared polymer was washed twice using appropriate amounts of methyl ethyl ketone and finally dried (yield 92%).

#### *2.2.3. Preparation of Fatty Esters Bromoacetate (Q8, Q10 And Q12)*

Fatty esters bromoacetate (Q8, Q10 and Q12) were prepared throughout reacting different fatty alcohols (0.1 mole) namely: octanol, decanol and dodecanol and bromoacetic acid (0.1 mole) in the



Elemental analysis: Vario Elementar Analyzer; FTIR spectroscopy: Perkin Elmer Genesis Fourier Transformer FTIR measured at 4000–400 ( $\text{cm}^{-1}$ ) applying potassium bromide compressed thin pellet technique. The nuclear magnetic resonance spectra were measured by Varian NMR-300, Mercury 300 MHz spectrometers using  $\text{CDCl}_3$  as solvent and trimethyl silane (TMS) as a reference to determine the different chemical shifts  $\delta$ (ppm); GPC measurements were performed using GPC-7890A instrument equipped with DB-23 column, 60 mm x 0.25 mm, i.d. of 0.25  $\mu\text{m}$ . TEM images were performed using TEM-JEOL JEM-2000, Germany.

### **2.3. Biological Activity**

The antimicrobial activity of synthesized cationic thiol polyurethane surfactants and their nanostructures with copper and nickel nanoparticles were measured against a wide range of test-organisms comprising: (bacteria and fungi)

#### *2.3.1. The Media*

The following media used in the antimicrobial activity of synthesized products, the bacterial species grow on nutrient agar, while fungi mold grow on Czapek's dox agar. (a) Nutrient agar: Nutrient agar consists of Beef extract (3.0 g/l); peptone (5.0 g/l), sodium chloride (3.0 g/l) and agar (20.0 g/l), then, completes the volume to 1 l, heated the mixture until the boiling and sterilizes the media by autoclave. (b) Czapek'sDox agar: Czapek'sDox agar consists of sucrose (20.0 g/l), sodium nitrate (2.0 g/l), magnesium sulfate (0.5 g/l), potassium chloride (0.5 g/l), ferrous sulfate (0.01 g/l) and agar (20.0 g/l), then, complete the volume to 1 l, heated the mixture until the boiling, and sterilize the media by autoclave.

#### *2.3.2. Microorganisms*

The different species of tested organisms were obtained from the unit of Operation Development Center, Egyptian Petroleum Research Institute. The used microorganisms were Gram-positive bacteria (*Bacillus subtilis* and *Staphylococcus aureus*), Gram-negative bacteria (*Salmonella typhimurium* and *Escherichia coli*), Yeast and Fungi (*Candida albicans* and *Aspergillus niger*). An assay is made to determine the ability of an antibiotic to kill or inhibit the growth of living microorganisms, the technique which used is: filter-paper disk-agar diffusion (Kirby-Bauer) are as the following [22]:

- Inoculate flask of melted agar medium with the organism to be tested.
- Pour this inoculated medium into a Petri dish.
- After the agar has solidified, a multilobed disk that impregnated with different antibiotics laid on top of agar.
- The antibiotic in each lobe of disk diffuses into medium and if the organism is sensitive to a particular antibiotic, no growth occur in a large zone surrounding that lobe (clear zone).
- The diameters of inhibition zones were measured after 24–48 h at 35–37 C (for bacteria) and 3–4 days at 25–27 C (for yeast and fungi) of incubation at 28 C
- Measure each clear zone and compare between them to determine the antibiotic which is more inhibitor.

Chloramphenicol, cycloheximide and cephalothin were used as reference drugs for gram-positive bacteria, gram-negative bacteria, and fungi, respectively.

Chloramphenicol is a broad spectrum antibiotic which acts as a potent inhibitor of bacterial protein biosynthesis. It has a long clinical history but bacterial resistance is common. Chloramphenicol footprinting studies with specific nucleotides has revealed the binding sites to be on the 50S ribosomal subunit where chloramphenicol interacts with the central loop of 23S rRNA domain V to inhibit peptidyl transferase activity [23].

Cycloheximide is a glutarimide antibiotic that inhibits protein biosynthesis in systems that utilize ribosomes of the 80 S type. The inhibition has been shown to involve one or more steps in the reaction sequence by which amino acids are transferred from aminoacyl transfer RNA into nascent peptides on ribosomes [24].

Cephalothin is bactericidal, effective against Gram-positive and Gram-negative bacterial species in vitro and in vivo, devoid of inherent toxicities and resistant to degradation by staphylococcal

penicillinase. Cephalothin is chemically related to the penicillins, but does not produce crossed allergic hypersensitivity reactions [25].

### 3. RESULTS AND DISCUSSION

#### 3.1. Chemical Structure

**Scheme 1** represents the preparation of cationicthiol polyurethane surfactants.

**Scheme 2** represents the preparation of nano cationic thiol polyurethane tetrahalo metallate.

The elemental analysis of the prepared cationic polyurethane surfactants (**Table 1**) showed the comparable values of the predicted and obtained ratios of the different elements in their chemical structure. The chemical structures of the prepared cationic polyurethane surfactants were confirmed using molecular weight measurements, elemental analysis, FTIR spectroscopy and <sup>1</sup>HNMR spectroscopy.

**Table1.** Elemental analysis of the synthesized cationic thiol polyurethane surfactants

| Compound | M.wt*<br>g/mole | Formula   | C%    |       | H%    |       | N%    |       | S%    |       | Br%   |       |
|----------|-----------------|---|-------|-------|-------|-------|-------|-------|-------|-------|-------|-------|
|          |                 |   | Calc. | Found | Calc. | Found | Calc. | Found | Calc. | Found | Calc. | Found |
| PQ8      | 20500           | (C <sub>45</sub> H <sub>78</sub> O <sub>14</sub> N <sub>4</sub> S <sub>2</sub> Br <sub>2</sub> ) <sub>n</sub> | 46.47 | 46.42 | 6.65  | 6.66  | 5.56  | 5.53  | 6.35  | 6.30  | 15.89 | 15.85 |
| PQ10     | 21400           | (C <sub>49</sub> H <sub>86</sub> O <sub>14</sub> N <sub>4</sub> S <sub>2</sub> Br <sub>2</sub> ) <sub>n</sub> | 48.54 | 48.50 | 7.05  | 7.06  | 5.27  | 5.25  | 6.02  | 5.98  | 15.05 | 15.01 |
| PQ12     | 22300           | (C <sub>53</sub> H <sub>94</sub> O <sub>14</sub> N <sub>4</sub> S <sub>2</sub> Br <sub>2</sub> ) <sub>n</sub> | 50.36 | 50.31 | 7.41  | 7.43  | 5.00  | 4.97  | 5.71  | 5.68  | 14.28 | 14.25 |

\* Obtained molecular weight from GPC measurements, n≈18.

##### 3.1.1. FTIR Spectroscopic Analysis


The chemical structures of the prepared cationic surfactants and their intermediates were confirmed using FTIR spectroscopic analysis.

FTIR spectra of triethanol amine mercaptoacetate showed the following absorption bands: broad absorption band centered at 3435 cm<sup>-1</sup> corresponds to -OH stretching; weak absorption band at 2550 cm<sup>-1</sup> corresponds to stretching of S-H group; absorption band at 2932 cm<sup>-1</sup> attributed to symmetric stretching of C-Hgroup; 1018 cm<sup>-1</sup> corresponds to C-N stretching group of aliphatic amine and absorption band at 1732 cm<sup>-1</sup> corresponds to C=O ester group.

Thiol polyurethane compound (**P**) showed the following absorption bands: 1663 cm<sup>-1</sup> corresponds to C=O of urethane group; 1458 and 1462 cm<sup>-1</sup> corresponds to N-H of urethane group; 1508-1510 cm<sup>-1</sup> described for the double bonds in the phenyl moiety (C=C) in toluene diisocyanate moiety (TDI).

FTIR spectra of alkyl bromoacetate esters (**Q8, Q10 and Q12**) represented the disappearance of the broad band at 3400 cm<sup>-1</sup> of alcoholic hydroxyl groups of the reacted fatty alcohols, the appearance of new absorption bands at: 1736-1738 cm<sup>-1</sup> corresponds to carbonyl ester indicates the ester (**Q8, Q10 and Q12**) formation; 1275-1277 cm<sup>-1</sup> corresponds to ether linkages C-O-C; 2920-2922 cm<sup>-1</sup> and 2849-2850 cm<sup>-1</sup> corresponded to symmetric and asymmetric stretching of C-H groups. The characteristic absorption band of C-Br bond was appeared in the range of 663-667 cm<sup>-1</sup>.


FTIR spectra of the prepared cationic thiol polyurethane surfactants (**PQ8, PQ10 and PQ12**) showed similar absorption bands to the absorption bands of triethanol amine mercaptoacetate, thiol polyurethane and alkyl bromoacetate esters. Furthermore, IR spectra recorded a disappearance of the absorption band at 660 cm<sup>-1</sup> and the appearance of a new absorption band at 3040 cm<sup>-1</sup> corresponded to C-N<sup>+</sup> group (**Figure 1**).



**Figure1.** IR spectra of cationic thiol polyurethane surfactant PQ10

### 3.1.2. $^1\text{H-NMR}$ Spectroscopic Analysis

The  $^1\text{H-NMR}$  spectra of the synthesized cationic surfactants (**Figure 2** for PQ10 as representative for the prepared surfactants) showed the appearance of signals at:  $\delta = 0.85$  ppm (t, 3H,  $\text{CH}_3$ ) assigned to terminal methyl group; 1.25 ppm (m, nH,  $\text{CH}_2$ ) attributed to the methylene groups of the fatty chains; 2.5 ppm (t, 3H,  $\text{CH}_3\text{Ph}$ ) assigned to methyl group of toluene diisocyanate moiety; 7.8 ppm, 8.0 ppm and 8.2 ppm (m, 4H, phenyl group).



**Figure2.**  $^1\text{H-NMR}$  spectra of cationic thiol polyurethane surfactant PQ10

### 3.1.3. Molecular Weight Measurements

The molecular weights of the prepared cationic surfactants were determined using GPC chromatographic measurements according to the methodology of our colleague [26]. The results showed that the surfactant molecules contain an average of 18 repeated units (exactly 17.8 units). The obtained values of the molecular weights of the different surfactants were listed in **Table 1**.

### 3.1.4. UV-Vis Spectroscopy

UV-Vis absorption spectra were used to determine the formation of copper and nickel nanoparticles stabilized by different cationic thiol polyurethane surfactants. UV-Vis absorption spectra of the prepared copper and nickel nanoparticles stabilized by different cationic thiol polyurethane surfactants were recorded in water as a solvent in order to monitor their formation and stability. Cationic thiol polyurethane surfactants with copper and nickel nanoparticles were confirmed by the appearance of new bands in UV spectra. UV-Vis spectroscopy is quite sensitive to the formation of copper and nickel nanoparticles due to surface Plasmon excitation.

UV spectrum of copper nanoparticles for characterizing the metallic nature whose broad peak corresponds to the Cu range from 350–550 nm [10].

UV spectrum of nickel nanoparticles for characterizing the metallic nature whose broad peak corresponds to the Ni range from 250–370 nm [27].

**UV-Vis spectra** shows absorption spectra of Cu NPs and Ni NPs capped by prepared cationic surfactants, which show absorption band listed in **table 2** which an indication on formation copper and nickel nanoparticles, due to surface Plasmon resonance of copper and nickel nanoparticles.


**Table2.** UV absorption maxima of copper and nickel nanoparticles with cationic thiol polyurethane surfactants

| Compounds    | $\lambda_{\text{max}}$ (nm) |
|--------------|-----------------------------|
| PQ8-Cu NPs   | 314, 389                    |
| PQ10- Cu NPs | 310, 400                    |
| PQ12- Cu NPs | 310, 402                    |
| PQ8-Ni NPs   | 224, 296                    |
| PQ10- Ni NPs | 220, 316                    |
| PQ12- Ni NPs | 210, 308                    |


Bands at  $\lambda_{\text{max}}$  range from 210 to 314 nm characteristic for the used capping agents, which matches with the band, appeared for aqueous solution of the used capping agents alone. It is known that the amount and size of copper and nickel nanoparticles are positively related with the adsorption peak intensity and the  $\lambda_{\text{max}}$  on the UV-Vis spectra respectively.

### 3.1.5. TEM Spectroscopy

TEM spectroscopy determines the size and morphology of the formed nanoparticles. The size and morphology of the prepared copper and nickel nanoparticles stabilized by cationic thiol polyurethane surfactants were investigated using transmission electron microscope (TEM), **Figures 3a and 3b** (as representative for the prepared copper and nickel nanoparticles). It is clear from TEM images that the copper and nickel nanoparticles stabilized by cationic thiol polyurethane surfactants are predominantly spherical in shape and polydispersed. The TEM image showed the self-assembling of the prepared surfactant on the copper and nickel nanoparticles which causes the stabilization of the nano size of these nanoparticles due to the formation of nano shells with the used surfactant.



**Figure 3a.** TEM images of Cu NPs with PQ12



**Figure 3b.** TEM images of Ni NPs with PQ12

### 3.2. Antimicrobial and Antifungal Activity of the Synthesized Cationic Surfactants and Their Nanostructures

The biological activities of the synthesized cationic surfactants (PQ8, PQ10 and PQ12) and their nanostructures with copper and nickel nanoparticles was screened against pathogenic Gram-positive (*Bacillus subtilis* and *Staphylococcus aureus*), Gram-negative (*Salmonella Typhimurium* and *Escherichia coli*), bacteria and also, some pathogenic fungi (*C. albicans* and *Aspergillus niger*) using the values of the inhibition zone diameter tests and the results are summarized in **Table 3**. Data in **Table 3** indicating that the synthesized compounds have antimicrobial activity rang from a moderate to slight high effect on Gram negative bacteria and Gram positive bacteria and moderate effect on fungi and high effect on yeast compared to the drug reference used.

**Table 3.** Antimicrobial activity of synthesized surfactants against pathogenic bacteria, yeast and fungi

| Compounds  | Bacteria                 |                              |                               |                         | Yeast                   | Fungi                    |
|------------|--------------------------|------------------------------|-------------------------------|-------------------------|-------------------------|--------------------------|
|            | Gram positive            |                              | Gram negative                 |                         |                         |                          |
|            | <i>Bacillus subtilis</i> | <i>Staphylococcus aureus</i> | <i>Salmonella typhimurium</i> | <i>Escherichia coli</i> | <i>Candida albicans</i> | <i>Aspergillus niger</i> |
| Control    | 26                       | 25                           | 28                            | 27                      | 28                      | 26                       |
| PQ8        | 15                       | 0                            | 0                             | 10                      | 17                      | 0                        |
| PQ10       | 17                       | 9                            | 0                             | 14                      | 19                      | 0                        |
| PQ12       | 22                       | 14                           | 0                             | 16                      | 24                      | 0                        |
| PQ8-Cu NPs | 20                       | 20                           | 17                            | 18                      | 15                      | 0                        |


## Antibacterial and Anti-Fungal Activity of (Tetrahalo Metallate) Copper and Nickel Nanoparticles Stabilized by Cationic Thiol Polyurethane Surfactants

|             |    |    |    |    |    |    |
|-------------|----|----|----|----|----|----|
| PQ10-Cu NPs | 29 | 21 | 21 | 26 | 18 | 16 |
| PQ12-Cu NPs | 35 | 41 | 33 | 32 | 23 | 16 |
| PQ8-Ni NPs  | 23 | 26 | 22 | 21 | 23 | 16 |
| PQ10-Ni NPs | 27 | 29 | 27 | 25 | 24 | 14 |
| PQ12-Ni NPs | 32 | 25 | 34 | 20 | 25 | 18 |

It is clear that the antimicrobial activities are gradually increased by increasing the hydrophobic chain length. The PQ12 surfactant showed the maximum antimicrobial activities against the tested bacterial strains. That behavior is depending on the surface activities of these biocides. Increasing the hydrophobic chain length increases the adsorption tendency of the biocide molecules at the various surfaces (water or microorganism's membranes). Hence, the potent action of the molecules is increased due to their high population at the cellular membrane [28-29].

General observation for data in **Table 3** indicates that the Gram-positive bacteria are more resistant to the tested compounds compared with the Gram-negative bacteria. The data provided from the inhibition zone diameter are describing the general behavior of the tested biocides against the different bacterial genera. The results of the antifungal activity obtained from the biological study showed promising features of the tested biocides against the most pathogenic fungal strain (*C. albicans*).

The bacterial cell membrane is composed of a thick wall containing many layers of peptidoglycan and teichoic acids, which are glycerol-ribitol (polyhydric alcohol) through a phosphorus bond surrounded by lipids of lipopolysaccharides and proteins [30]. In Gram positive bacteria (**Figure 4**), the adsorption is occurred in the lipoteichoic acid layer which is characterized by the charged nature and the ability to interact with the positively charged molecules. While in the Gram-negative bacteria (**Figure 4**), the lipid layer (highly non polar layer) is the target of the positively charged biocide molecules. So the mode of action of that type of compounds on different microorganisms can be attributed to the adsorption of amphiphile molecules on the outer cellular membrane of the microorganism due to their amphipathic characteristics. In addition the similarity between the hydrophobic chains and the lipid layers and the building units of the cell membranes and the monosaccharide in these compounds [31]. As a result of that adsorption, the molecules penetrate through the cell membrane; furthermore the positive charges in the cationic molecules neutralize the negative charges on the bacterial cell membranes. Accordingly, the selective permeability which characterizes the outer cellular membrane is completely deactivated [32].



**Figure4.** Structure of the bacterial cell walls

Hence, the vital transportation of essential components, bioreactions and activities of the cell are disturbed, causing death for these microorganisms.

By inspection data in **Table 3**, the biological activity of copper and nickel nanoparticle stabilized by synthesized cationic surfactants higher than corresponding synthesized cationic surfactants, this can be attributed to copper and nickel nano particle alone have biological activity, so prepared surfactant capped copper and nickel nanoparticles have higher activity, this can be attributed to the higher surface area of prepared nanoparticles. In addition to the bactericidal effect of metal nanoparticles has been attributed to their small size and high surface to volume ratio, which allows them to interact closely with microbial membranes and is not merely due to the release of metal ions in solution. A



cell wall is present around the outside of the bacterial cell membrane and it is essential to the survival of bacteria.

#### **4. CONCLUSION**

The main conclusions are as the following:

- The results indicate formation and stabilization of copper and nickel nanoparticle using synthesized cationic surfactants.
- By increasing the hydrophobic chain length of the synthesized cationic surfactants, the stability of prepared CuNPs and NiNPs increase.
- The antimicrobial activities of the compounds toward bacteria and fungi were high compared to the drug used.
- The antimicrobial and anti-fungal activity depended on the chemical structure of the synthesized surfactants and their nanostructure.
- The copper nanoparticles of the stabilized surfactants increase their biological activity more than nickel nanoparticles.

#### **REFERENCES**

- [1] Thomas, F.G, Zongyu, Z., Hyun-Jung, K., Debjani, M., Ying, X., Daniel, P.P., Byron, F.B., Richard C.L. and Michael, R.K. Thermo-Mechanical and Antibacterial Properties of Soybean Oil-Based Cationic Polyurethane Coatings: Effects of Amine Ratio and Degree of Crosslinking. *Macromol. Mater. Eng.*, 2014, **299**: 1042–1051.
- [2] Ren, J.Y., Zheng, Y.M., Lin, Z.H., Han, X. and Liao, W.Z. Macroporous resin purification and characterization of flavonoids from *Platycladus orientalis* (L.) Franco and their effects on macrophage inflammatory response. *Food Funct.*, 2017, **8**: 86–95.
- [3] Haiyan, L., Lingxiao, L., Jingyi, L., Moutong, C. and Chaoqun, Z. Bio-based cationic waterborne polyurethanes dispersions prepared from different vegetable oils. *Industrial Crops & Products*, 2018, **117**: 169–178.
- [4] Lee, H., Lee, G., Jang, N., Yun, J., Song, J. and Kim, B. Biological synthesis of copper nanoparticles using plant extract. *Nanotechnology*, 2011, **1**: 371- 374.
- [5] Majumder, D. Bioremediation: Copper Nanoparticles from Electronic-waste. *Inter. J. of Eng. Science and Technology*, 2012, **4**: 4380-4389.
- [6] Shrikaant, K. Biosynthesis and Characterization of Copper Metal Nanoparticles Using Ascorbic Acid. *Chemical Science Transactions*, 2015, **4**: 922-926.
- [7] Pergolese, B., Miranda Muniz, M. and Bigotto, A. Study of the Adsorption of 1,2,3-Triazole on Silver and Gold Colloidal Nanoparticles by Means of Surface Enhanced Raman Scattering. *J. Phys. Chem. B*, 2006, **110**: 9241–9247.
- [8] Toimil-Molares, M.E., Buschmann, V., Dobrev, D., Neumann, R., Scholz, R., Schuchert, I.U. and Vetter, J. Single-crystalline copper nanowires produced by electrochemical deposition in polymeric ion track membranes. *Adv. Mater.*, 2001, **13**: 62-69.
- [9] Toimio-Molares, M.E., Hohberger, E.M., Schaefflein, C., Blick, R.H., Neumann, R. and Trautmann, C. Electrical characterization of electrochemically grown single copper nanowires. *Appl. Phys. Lett.*, 2003, **82**: 2139-2147.
- [10] Subhankari, I. Antimicrobial Activity of Copper Nanoparticles Synthesised by Ginger (*Zingiber officinale*) Extract. *World Journal of Nano Science & Technology*, 2013, **2**: 10-13.
- [11] Ki-Young, Y., Jeong Hoonm, B., Jae-Hong P. and Jungho, H. Susceptibility constants of *Escherichia coli* and *Bacillus subtilis* to silver and copper nanoparticles. *Science of the Total Environment*, 2007, **373**: 572-575.
- [12] Raffi, M., Mehrwan, S., Bhatti, T.M., Akhter, J.I., Hameed, A. and Yawar, W. Investigations into the antibacterial behavior of copper nanoparticles against *Escherichia coli*. *ann Microbiol.*, 2010, **60**: 75–80.
- [13] Rispoli, F., Angelov, A., Badia, D., Kumar, A., Seal, S. and Shah, V. Understanding the toxicity of aggregated zero valent copper nanoparticles against *Escherichia coli*. *J Hazard Mater.*, 2010, **180**: 212–216.
- [14] Ravishankar, R.V. and Jamuna B.A. Nanoparticles and Their Potential Application as Antimicrobials. *Science against Microbial Pathogens: Communicating Current Research and Technological Advances. In Méndez-Vilas, A., Ed., Formatex, Microbiology* 2011, Series, No. 3, Vol. **1**, Spain, 197-209.

- [15] Negm, N.A. and Mohamed, A.S. Synthesis, characterization and biological activity of sugar-based gemini cationic amphiphiles. *J SurfactDeterg.*, 2008, **11**:215-221.
- [16] Shokry, S.A., El Morsi, A.K., Sabaa, M.S., Mohamed, R.R. and El Sorogy, H.E. Synthesis and characterization of polyurethane based on hydroxyl terminated polybutadiene and reinforced by carbon nanotubes. *Egypt J Petrol.*, 2015, **24**:145-54.
- [17] Negm, N.A. and Morsy, S.M.I. Corrosion inhibition of triethanolammonium bromide mono- and dibenzoate as cationic inhibitors in an acidic medium. *J SurfactDeterg.*, 2005, **8**: 283-287.
- [18] Zaki, M.F., Badawi, A.M., Sabbah, I.A., Abdelghani, R.A. and Hendawy, M.E. Synthesis, Characterization and Surface Activities of Cationic Polysaccharide (Aloe) Schiff Base Surfactants. *J SurfactDeterg.*, 2015, **18**:455-461.
- [19] Negm, N.A., El Hashash, M.A., Youssif, M.A., Ismail, E.A., Abdeen, Z.I. and Abdel Rahman, N.R. Novel Nonionic Polyurethane Surfactants and Ag Nanohybrids: Influence of Nonionic Polymeric Chains. *J SurfactDeterg.*, 2017, **20**:173-182.
- [20] Saleh, N., Khowdiary, M. and Badawi, A.M. Synthesis and Antitumor and Surface Activity of Novel Tetrachloro Metallate Complexes of Sulfaquinoxaline with Co(II), Cu(II), or Sn(II) Chlorides, *Tenside Surf. Det.*, 2014, **51**: 4-15.
- [21] Sara Busi, Manu Lahtinen, Jussi Valkonen and Kari Rissanen. Crystal structures and thermal behavior of bis[dibenzyl dimethylammonium]CuBr<sub>4</sub>, bis[dibenzyl dimethylammonium]CuCl<sub>4</sub> and bis[dimethyldi(2 phenylethyl)ammonium]CuBr<sub>4</sub> crystallized from acetonitrile and dilute HX (X=Cl or Br) solutions, *Journal of Molecular Structure*, 2006, **794**: 277-287.
- [22] Muanza, D.N., Kim, B.W., Euler, K.L. and Williams, L. Antibacterial and Antifungal Activities of Nine Medicinal Plants from Zaire. *Int. J. Pharmacogn.*, 1994, **32**: 337-345.
- [23] Weiling, H., Jie, Z. and Jianping, X. Antibiotic drugs targeting bacterial RNAs. *Acta Pharmaceutica Sinica B.*, 2014, **4**(4): 258-265.
- [24] Tom, G.O., William J.C., Wallace, L.M. and Hardesty, B. The Mechanism by which Cycloheximide and Related Glutarimide Antibiotics Inhibit Peptide Synthesis on Reticulocyte Ribosomes. *Journal of biological chemistry*, 1971, **246**: 174-181.
- [25] Boniece, W.S., Wick, W.E., Holmes, D.H. and Redman, C.E. In vitro and in vivo laboratory evaluation of cephalothin: A broad spectrum antibiotic. *J. Bact.*, 1962, **84**: 1292-1296.
- [26] Azzam, E.M.S., El-Farrage, A.F.M., Ismail, D.A. and Abd-Elaal, A.A. Enhancement of the surface activity for some monomeric and polymeric thiol surfactants using silver nanoparticles. *J DispSci Technol.*, 2011, **32**: 816-822.
- [27] Sulekh Chandra, Avdhesh Kumar and Praveen Kumar Tomar. Synthesis of Ni nanoparticles and their characterizations. *Journal of Saudi Chemical Society*, 2014, **18**: 437-442.
- [28] Cukurovali, A., Yilmaz, I., Gur, S. and Kazaz, C. Synthesis, antibacterial and antifungal activity of some new thiazolyldrazone derivatives containing 3-substituted cyclobutane ring. *Eur. J. Med. Chem.*, 2006, **41**: 201-207.
- [29] Negm, N.A., Morsy, S.M.I. and Said, M.M. Biocidal activity of some Mannich base cationic derivatives. *Bioorg. Med. Chem.*, 2005, **13**: 5921-5926.
- [30] Walsh, F. and Amyes, S. Microbiology and drug resistance mechanisms of fully resistant pathogens. *Curr Opin Microbiol*, 2004, **7**:439-444.
- [31] Chernomordik, I., Kozlov, M.M. and Zimmerberg, J. Lipids in biological membrane fusion. *J Membr Biol.*, 1995, **146**:1-14.
- [32] Saier, M.H., Jr. Enzymes in metabolic pathways. Harper & Row, New York 1987.

**Citation:** Mostafa E. Hendawy, (2018). "Antibacterial and Anti-Fungal Activity of (Tetrahalo Metallate) Copper and Nickel Nanoparticles Stabilized by Cationic Thiol Polyurethane Surfactants", *International Journal of Petroleum and Petrochemical Engineering (IJPPE)*, 4(4), pp.42-51, DOI: <http://dx.doi.org/10.20431/2454-7980.0404005>

**Copyright:** © 2018 Authors. This is an open-access article distributed under the terms of the Creative Commons Attribution License, which permits unrestricted use, distribution, and reproduction in any medium, provided the original author and source are credited